

DUPONT™ TYVEK® 1443R

PRODUCT PROPERTIES—METRIC UNITS

Product Features:
Antistatic Treatment
Corona Treated

Specification Properties (Metric Units)

Property	Comparable Test Method	Units	Tyvek® 1443R
Basis Weight	ASTM D3776 ¹ EN ISO 536 ¹	g/m ²	43 [41–45]
Delamination	ASTM 2724 ²	N/2.54 cm	0.58 [0.18 minimum]

Notes: Specification properties are based on roll averages from samples taken uniformly across the sheet. Specification properties are controlled to a nominal value and released within specification; the ranges listed represent the controlled minimum and maximum values in which the product is released. The customer is responsible for determining that Tyvek® is suitable for the intended application.

1. Modified for sample size.
2. Modified for speed and sample width.

Miscellaneous Properties (Metric Units)

Property	Comparable Test Method	Units	Tyvek® 1443R
Thickness	ASTM D1777 ¹ EN ISO 534 ¹	µm	155
Tensile Strength, MD	ASTM D5035 ² EN ISO 1924 ²	N/2.54 cm	49
Tensile Strength, CD	ASTM D5035 ² EN ISO 1924 ²	N/2.54 cm	48
Elongation, MD	ASTM D5035 ² EN ISO 1924 ²	%	11
Elongation, CD	ASTM D5035 ² EN ISO 1924 ²	%	20
Tongue Tear, MD	ASTM 2261 ³	N	9.8
Tongue Tear, CD	ASTM 2261 ³	N	9.8
Mullen Burst	ASTM D774 ISO 2758	KPa	359

Notes: Miscellaneous properties are typical values based on roll averages from samples taken uniformly across the sheet. Miscellaneous properties are not controlled in the process; therefore, they are subject to slight change from normal process drift.

MD = machine direction; CD = cross direction.

1. Area = 2 cm²; pressure = 50 kPa
2. Modified for speed and gauge length.
3. Integration average method. Modified for speed and gauge length.

For more information about DuPont™ Tyvek®, call us today at 1.800.44.TYVEK

This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is intended for use by persons having technical skill for evaluation under their specific end-use conditions at their own discretion and risk. Since conditions of use are outside our control, WE MAKE NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATIONS, NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE AND ASSUME NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION.

This information is not intended as a license to operate under or a recommendation to infringe any patent, trademark, or technical information of DuPont or others covering any material or its use.

Copyright © 2017 DuPont. All rights reserved. The DuPont Oval Logo, DuPont™, and Tyvek® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. K-29469 (3/17)

DUPONT™ TYVEK® 1443R

PRODUCT PROPERTIES—ENGLISH UNITS

Product Features:
Antistatic Treatment
Corona Treated

Specification Properties (English Units)

Property	Comparable Test Method	Units	Tyvek® 1443R
Basis Weight	ASTM D3776 ¹ EN ISO 536 ¹	oz/yd ²	1.27 [1.20–1.33]
Delamination	ASTM 2724 ²	lb _f /inch	0.13 [0.04 minimum]

Notes: Specification properties are based on roll averages from samples taken uniformly across the sheet. Specification properties are controlled to a nominal value and released within specification; the ranges listed represent the controlled minimum and maximum values in which the product is released. The customer is responsible for determining that Tyvek® is suitable for the intended application.

1. Modified for sample size.
2. Modified for speed and sample width.

Miscellaneous Properties (English Units)

Property	Comparable Test Method	Units	Tyvek® 1443R
Thickness	ASTM D1777 ¹ EN ISO 534 ¹	mils	6.1
Tensile Strength, MD	ASTM D5035 ² EN ISO 1924-2 ²	lb _f /inch	10.9
Tensile Strength, CD	ASTM D5035 ² EN ISO 1924-2 ²	lb _f /inch	10.7
Elongation, MD	ASTM D5035 ² EN ISO 1924-2 ²	%	11
Elongation, CD	ASTM D5035 ² EN ISO 1924-2 ²	%	20
Tongue Tear, MD	ASTM 2261 ³	lb _f	2.2
Tongue Tear, CD	ASTM 2261 ³	lb _f	2.2
Mullen Burst	ASTM D774 ISO 2758	psi	52

Notes: Miscellaneous properties are typical values based on roll averages from samples taken uniformly across the sheet. Miscellaneous properties are not controlled in the process; therefore, they are subject to slight change from normal process drift.

MD = machine direction; CD = cross direction.

1. Area = 0.625 in²; pressure = 7.15 psi
2. Modified for speed and gauge length.
3. Integration average method. Modified for speed and gauge length.

For more information about DuPont™ Tyvek®, call us today at 1.800.44.TYVEK

This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is intended for use by persons having technical skill for evaluation under their specific end-use conditions at their own discretion and risk. Since conditions of use are outside our control, WE MAKE NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATIONS, NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE AND ASSUME NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION.

This information is not intended as a license to operate under or a recommendation to infringe any patent, trademark, or technical information of DuPont or others covering any material or its use.

Copyright © 2017 DuPont. All rights reserved. The DuPont Oval Logo, DuPont™, and Tyvek® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. K-29469 (3/17)